



Cementitious Coating 851

Waterproofing and Protection of Concrete



Product Overview

Two component, polymer modified, cementitious waterproof coating. CE-marked in accordance with BS EN 1504-2.

Uses

Internal and external structural waterproofing of concrete and other mineral substrates. Provides chloride protection on highway and coastal structures and enhances the durability of reinforced concrete by reinstating effective concrete cover to achieve the specified design life. Suitable for surface protection systems principles 1.3, 2.2, 8.2 as defined in BS EN 1504-2.

Advantages

- Incorporates the latest proven cement chemistry, microsilica, fibre and styrene acrylic copolymer technology.
- Pre-packaged material only requiring mixing on-site.
- Brush, trowel or spray applied normally in two coats. Roofs and decks only require a single coat application.
- Excellent adhesion to sound prepared concrete.
- Dense matrix offers low permeability to water at 10 bar positive and negative pressure and very high diffusion resistance to a carbon dioxide gas and chloride ions.
- Provides the equivalent of 100mm of good quality concrete cover.
- Can be applied on green concrete.
- Protects concrete in sulphate contaminated ground conditions.
- Non-toxic when cured and listed as authorised for use under Regulation 31 for use in the supply of drinking water.
- Easily overcoated with specialist membranes to provide further protection and aesthetic properties.

Description

CEMENTITIOUS COATING 851 is a two component, thixotropic, polymer modified, cementitious waterproofing coating. It cures to form a hard, durable, highly alkaline coating with a degree of elasticity which protects concrete and other mineral substrates from the effects of water ingress, chlorides, and carbonation. It provides economic reinstatement of cover on newly cast concrete to ensure the design life is achieved, and to extend the service life of existing structures.

Compliance

- CE-marked in accordance with BS EN 1504-2. Suitable for surface protection systems principals 1.3, 2.2, 8.2 as defined in BS EN 1504-2.
- BBA Approved, Certificate No. 05/4276.
- Listed under Regulation 31 – England and Wales; Regulation 33 – Scotland; Regulation 30 - NI: for use with potable water.
- Compliant with LU Standard 1-085 'Fire Safety Performance of Materials'.

Specification Clause

The structural waterproofing coating shall be a two component, thixotropic, polymer modified cementitious coating. It shall be CE-marked in accordance with BS EN 1504-2 and shall be impermeable to water under 10 bar hydrostatic pressure such that a 2.0mm coating is equivalent to 1000mm of concrete. It shall exhibit Chloride Ion diffusion resistance with at least 31 years' independent testing to confirm performance.

CE
2797

Flexcrete Technologies Ltd
Tomlinson Road, Leyland PR25 2DY England
17
2797-CPD-530942
EN1504-2: Surface Protection Systems - Coating
Protection against Ingress (PIC) Rigid trafficked system

Compressive Strength	: Class I ≥ 35 MPa
Permeability to CO ₂	: Equiv. to 100mm of concrete
Permeability to Water Vapour	: Class I < 5m
Capillary Absorption	: Class III < 0.1 kg.m ⁻² .h ^{0.5}
Coefficient of Thermal Exp.	: ≤ 30 x 10 ⁻⁶ .K ⁻¹
Therm. Comp. EN 13687-1	: > 2.0 MPa
Adhesive Bond	: ≥ 2.0 MPa
Dangerous Substances	: Complies with 5.4
Reaction to Fire	: Euroclass A2-s1, d0
Chloride Ion Diffusion (UK)	: Steady state not reached after 31 years on test



Technical Data

Property	Standard	BS EN 1504-2 Requirement	Typical Results
Compressive Strength	EN 12190	≥ 35 MPa (Class 1) Traffic with Polyamide wheels	28 days: 40.0MPa
Compressive Strength Development @20°C	BS4551		1 day 10.5MPa 7 days 30.5MPa 28 days 40.0MPa
Adhesive Bond	EN 1542	≥ 2.00 MPa	2.07MPa
Chloride Ion Diffusion Resistance	Vinci Test		No steady state of flux reached after 31 years on test
Permeability to CO ₂	EN 1062-6	R≥ 50m	2mm equivalent to 100mm of concrete
Permeability to Water Vapour	BS EN ISO7783-2	Class 1: S _D ≤ 5m	S _D = 0.91m
Thermal Compatibility	EN13687-1	≥ 2.00 MPa	3.5MPa
Water Permeability Coefficient Equivalent Concrete Thickness	Vinci Test		6.00 x 10 ⁻¹⁶ m/sec 2mm = 1000mm of concrete
Resistance to Water Pressure	DIN 1048		10 bar (100m hydrostatic head) positive and negative)
Coefficient of Thermal Expansion	EN1770	≤ 30 x 10 ⁻⁶ K ⁻¹	16.6 x 10 ⁻⁶ K ⁻¹
Tensile Strength	BS 6319:7		2.66 MPa
Wear Resistance	EN13813		Exceeds BCA AR0,5: Highest classification of wear resistance.
Liquid Water Transmission Rate (Capillary Absorption and Permeability to Liquid water)	EN1062-3	Class III (low) w<0.1kg.m ⁻² .h ^{0.5}	w = 0.018kg.m ⁻² .h ^{-0.5}
Reaction to Fire	EN 13501-1	Euroclass	Euroclass A2 – s1, d0
Mixed Colour			Concrete Grey and White
Mixed Density			1800 kg/m ³
Application Thickness			2mm in 1 or 2 coats
Minimum Application Temp			≥3°C on a rising thermometer ≥5°C on a falling thermometer
Working Life (approx.)			30 minutes at 20°C
Overcoat Time			30-90 minutes depending on temperature

The properties given above are obtained from laboratory tests: results obtained from on-site testing may vary according to site conditions

Application Instructions

Preparation

The areas to be treated must be free from all unsound material, dust, oil, grease, corrosion by-products and organic growth.

Smooth surfaces should be roughened, all loose material and surface laitance removed. Any defective concrete should be reinstated with the appropriate Flexcrete repair mortar.

The strength of the concrete sub-base should be a minimum of 20MPa.

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without any standing water.

Any active water infiltration must first be stopped using **FASTFILL WP**.

Substrate Priming

All roof and deck applications must be primed with **CEMPROTEC EF PRIMER**. In drinking water applications, use **POLYMER ADMIXTURE 850** diluted with clean water (See separate Data Sheets for further information). Other highly porous substrates may benefit from additional sealing with **CEMPROTEC EF PRIMER**.

Mixing

CEMENTITIOUS COATING 851 is supplied as a two pack, Part A liquid and Part B powder. **The two components MUST NOT be split. All of Part A and all of Part B MUST be mixed.**

Shake Part A (liquid) and pour into a suitable mixing vessel. Slowly add the Part B (powder) and mix for a minimum of 5 minutes until homogenous, without any lumps. Mixing should be carried out using a slow-speed





drill and paddle designed to entrap as little air as possible.

Please Note: These instructions must be strictly adhered to. Flexcrete cannot be held responsible for any product failures due to incorrect mixing.

Placing

CEMENTITIOUS COATING 851 is applied using brush, trowel or spray techniques. Care should be taken to ensure that air is not entrapped onto the surface.

For vertical and overhead applications, apply in 2 x 1mm thick coats, applying the second coat when the first coat is stable but not fully set (typically 30-90 minutes depending on temperature). On horizontal applications (roofs or decks) apply in a single 2mm thick layer, spreading with a notched trowel, squeegee or skid leveller, and immediately use a spiked roller to remove entrapped air.

Detail Work

Where movement is anticipated around penetrations and over joints or cracks, apply a 1mm thick stripe coat of **CEMENTITIOUS COATING 851** by brush and immediately embed **CEMPROTEC 2000-S** tape. Allow to stabilise before proceeding with the main application.

Curing

Normal concreting procedures should be strictly adhered to. It is important that the surface of the coating is protected from strong sunlight and drying winds with **CURING MEMBRANE WB**. On roofs or decks **CEMPROTEC EF GRIT** can be broadcast onto the surface of the wet coating to provide effective curing, whilst also providing an abrasion and slip-resistant finish. In exposed conditions, curing **MUST** commence immediately as work progresses.

Important Notes

- CEMENTITIOUS COATING 851** is not a decorative finish and may temporarily discolour until uniformly weathered. Can be overcoated with Flexcrete membranes to give a coloured finish.
- When applying in a tidal zone, allow to cure typically for a minimum of 2 hours before being immersed. Protect from abrasion or aggressive tidal flow if necessary.
- When treating potable water structures please refer to the IFU Document (contact Technical Dept).

Cleaning and Storage

All tools should be cleaned with water immediately after use. Materials can be stored for 12 months in dry, frost free conditions with unopened packaging at 20°C.

Packaging

CEMENTITIOUS COATING 851 is supplied in a 30kg composite pack.

Coverage and Yield

15.4 litres per 30kg pack.

A 30kg pack will cover approximately 7.7m² at 2mm thickness.

Health and Safety

Safety Data Sheets are available on request.

Application Top Tips

- Regularly check the coating thickness during application using a wet film thickness gauge.
- Apply **CURING MEMBRANE WB** as an even fine mist spray. Do not over apply or allow to pond on the surface or cracking may occur.
- CEMENTITIOUS COATING 851** is not a decorative coating and may dry with a patchy appearance until uniformly weathered. It can be overcoated with Flexcrete membranes to give a coloured finish.
- When broadcasting **CEMPROTEC EF GRIT** use techniques so that the particles are projected upwards to fall evenly without disrupting the smooth surface of the coating. Use a grit blower on larger areas.
- In cold, humid conditions condensation may form on surfaces treated with **CEMENTITIOUS COATING 851**, resulting in darkening of the finish and retardation of set.
- Please consult our Technical Department when waterproofing underneath road asphalt.
- Seal sanded surfaces with **CEMPROTEC SANDSEAL WB**.
- Cold Weather Working (See separate Guide): minimum application temperatures:
 - Do not use any Part A which has been frozen.
 - When applying to potable water structures the minimum application temperature is 7°C: see IFU document for full information.**
- Hot Weather Working (See separate Guide)
 - Store material in cool conditions to maximise working life.
 - Shade applied material from strong sunlight.
 - Spray apply a second mist coat of **CURING MEMBRANE WB**.
 - If possible, avoid extreme temperatures by working at night.

The information herein is correct to the best of our knowledge, but it does not necessarily refer to the particular requirements of the customer. If the customer has any particular requirements it should make them known in writing to Flexcrete Technologies Limited, and obtain further advice accordingly.

